

**Product Specification - Biaxial Geogrid BXGRID12 Type 2**

Phone: 281-717-8921

[www.siltmanagementsupplies.com](http://www.siltmanagementsupplies.com)

<b>Product Type:</b>	Integrally Formed Biaxial Geogrid		
<b>Polymer:</b>	Polypropylene		
<b>Load Transfer Mechanism:</b>	Positive Mechanical Interlock		
<b>Primary Applications:</b>	Spectra System (Base Reinforcement, Subgrade Improvement)		
<b>Index Properties</b>	<b>Units</b>	<b>MD Values<sup>1</sup></b>	<b>XMD Values<sup>1</sup></b>
Aperture Dimensions <sup>2</sup>	mm (in)	25 (1.0)	33 (1.3)
Minimum Rib Thickness <sup>2</sup>	mm (in)	1.27 (0.05)	1.27 (0.05)
Tensile Strength @ 2% Strain <sup>3</sup>	kN/m (lb/ft)	6.0 (410)	9.0 (620)
Tensile Strength @ 5% Strain <sup>3</sup>	kN/m (lb/ft)	11.8 (810)	19.6 (1,340)
Ultimate Tensile Strength <sup>3</sup>	kN/m (lb/ft)	19.2 (1,310)	28.8 (1,970)
<b>Structural Integrity</b>			
Junction Efficiency <sup>4</sup>	%	93	
Flexural Stiffness <sup>5</sup>	mg-cm	750,000	
Aperture Stability <sup>6</sup>	m-N/deg	0.65	
<b>Durability</b>			
Resistance to Installation Damage <sup>7</sup>	%SC / %SW / %GP	95 / 93 / 90	
Resistance to Long Term Degradation <sup>8</sup>	%	100	
Resistance to UV Degradation <sup>9</sup>	%	100	

**Dimensions and Delivery:** The biaxial geogrid shall be delivered to the jobsite in roll form with each roll individually identified and nominally measuring 3.0 meters (9.8 feet) or 4.0 meters (13.1 feet) in width and 50.0 meters (164 feet) in length. A typical truckload quantity is 160 to 210 rolls.

**Notes:**

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
2. Nominal dimensions.
3. Determined in accordance with ASTM D6637-10 Method A.
4. Load transfer capability determined in accordance with ASTM D7737-11.

**Product Specification - Biaxial Geogrid BXGRID12 Type 2**

Phone: 281-717-8921

[www.siltmanagementsupplies.com](http://www.siltmanagementsupplies.com)

5. *Resistance to bending force determined in accordance with ASTM D7748-12, using specimens of width two ribs wide, with transverse ribs cut flush with exterior edges of longitudinal ribs, and of length sufficiently long to enable measurement of the overhang dimension.*
6. *Resistance to in-plane rotational movement measured by applying a 20 kg-cm (2 m-N) moment to the central junction of a 9-inch x 9-inch specimen restrained at its perimeter in accordance with GRI GG9*
7. *Resistance to loss of load capacity or structural integrity when subjected to mechanical installation stress in clayey sand (SC), well graded sand (SW), and crushed stone classified as poorly graded gravel (GP). The geogrid shall be sampled in accordance with ASTM D5818 and load capacity shall be determined in accordance with ASTM D6637.*
8. *Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing*
9. *Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.*

*It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.*

*Made in the USA*

*Manufactured By: L & M Supply Co., Inc.*