



SPECIFICATION PAGE

Product Name: US-2SRD - Double Net Straw Blanket (rapid degradable)

Manufacturer: US Erosion Control Products inc., an L & M Supply Company (Phone: 800-948-7870)

Physical Description:

Size:	Available in a 8' + 16' widths by 112.5' + 562.5' lengths.
Netting: Top & Bottom	2 layers of 0.588" x 0.5" opening, approximately 15 lbs/1000sqyds photodegradable polypropylene plastic.
Thread:	800 denier degradable split yarn.
Matrix:	100% agricultural cured wheat straw, 0.5 lbs/sy.
Packaging:	All rolls are wrapped tightly with stretch wrap to protect the rolled erosion control product from the weather and elements.
Special Features:	US-2SRD has a 4" folded edge on both sides of the 8' width creating a stronger blanket and a cleaner edge.

Recommended Applications:

US- 2SRD is recommended for use on slopes up to 2:1 and in medium flow channels with a functional longevity of up to 60-90 days.

Recommended Installation Pattern:

The leading edge is to be trenched into a 6" deep trench and the blanket is to be placed parallel to the anticipated water flow. When more than 1 blanket is required, they are to be overlapped 6" on all overlapping sides and tiled in a shingle type pattern as to not let the water underneath the blanket.

Test Data:

Test Method - Description	Parameters	Test Result
ASTM D 6475 - Mass per Unit Area	Index Test	9.49 oz/sq.yd.
ASTM D 6818 - Ultimate Tensile Strength / Strain-TD	Index Test	12.9 lb/in @ % 31.0 8.0 lb/in @ % 30.0
ASTM D 6525 - Thickness	Index Test	340 mils
ASTM D 6567 - Ground Cover / Light Penetration	Index Test	91.2 % / % 8.8
ASTM D 1117 & ECTC-TASC 00197 - Water Absorption	Index Test	300%
ASTM D 7101 - Determination of Un-vegetated RECP Ability to Protect Soil from Rain Splash and Associated Runoff under Bench-Scale Conditions	50 mm (2 in.) / hr for 30 min. 100 mm (4 in.) / hr for 30 min. 150 mm (6 in.) / hr for 30 min.	Soil Loss Ratio* = 14.94 Soil Loss Ratio* = 15.43 Soil Loss Ratio* = 15.93
ASTM D 7207 - Determination of Un-vegetated RECP Ability to Protect Soil from Hydraulically-Induced Shear Stresses Under Bench-Scale Conditions	Shear: 1.82 psf for 30 min. Shear: 2.39 psf for 30 min. Shear: 2.96 psf for 30 min. Soil loss curve intercept =	Soil Loss = 301.7 g Soil Loss = 570.0 g Soil Loss = 1168.3 g 2.17 psf @ 1/2-in soil loss
ASTM D 7322 - Determination of Temporary Degradable RECP Performance in Encouraging Seed Germination and Plant Growth	Top soil; Fescue (Kentucky 31) 21 day incubation; 27±2° & approximately 45±5% RH	<u>% of Control</u> 440% (increased biomass)