



G100N G-Series Drainage Composite

G100N Drainage Composite is produced from a high compressive strength polystyrene core with a Mirafi® 140N nonwoven filter geotextile bonded to one side.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

Core Mechanical Properties	Test Method	Unit	Typical Roll Value
Thickness	ASTM D1777	in (mm)	0.4 (10)
Compressive Strength	ASTM D1621	psf (kPa)	18,000 (862)
Flow Rate ¹	ASTM D4716	gal/min/ft (l/min/m)	21 (261)

¹ In plane flow rate at 172 kPa (3600 psf) with a gradient of 1.0

Mechanical Properties for Mirafi® 140N	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	130 (578)	130 (578)
Grab Tensile Elongation	ASTM D4632	%	70	70
CBR Puncture Strength	ASTM D6241	lbs (N)	360 (1550)	
			Maximum Opening Size	
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	70 (0.212)	
			Minimum Roll Value	
Permittivity	ASTM D4491	sec ⁻¹	2.1	
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	150 (6113)	
			Minimum Test Value	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70	
Physical Properties		Unit	Typical Value	
Roll Dimensions (width x length)		ft (m)	4.0 x 50 (1.2 x 15.2)	
Roll Area		ft ² (m ²)	200 (18.6)	
Estimated Roll Weight		lb (kg)	50 (23)	

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi® is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.